

The most widely used girth weld protection system for three-layer coated pipes.

## Product description

### HTLP80 field-joint coatings.

**Construction:** Three-layer system:

**First layer:** Liquid epoxy, solvent-free two-component.

**Second layer:** High shear strength copolymer adhesive.

**Third layer:** Radiation cross-linked, high density polyethylene with **PCI** (Permanent Change Indicator).

The HTLP80 system is a wrap-around heat-shrinkable sleeve which replicates the structure and performance of mill-applied three-layer PE coatings. HTLP80 also has excellent compatibility and has been extensively used on many other mill-applied coatings (see below). By far the majority of the girth welds worldwide on three-layer coated pipes, diameters up to 100" (DN2500), have been coated with HTLP80.

During installation, the epoxy is applied to the prepared pipe surface and the heat-shrinkable sleeve is immediately wrapped around the joint over the wet epoxy. Heat is then applied to the sleeve which shrinks to form a tight fit around the joint. While curing, the epoxy forms strong mechanical and chemical bonds to the pipe surface & to the copolymer adhesive layer. The radiation cross-linked outer layer forms a tough barrier against mechanical damage and moisture transmission.

## Product features/benefits

- Fully resistant to shear forces induced by soil and thermal movements**  
The HTLP is tough & lasts as long a 3-layer, mill-applied coating.
- Sleeve applied over wet epoxy---allowing formation of strong mechanical & chemical bonds**  
Allows fast application, combined with high performance!
- Superior cathodic disbondment and hot water immersion resistance**  
Offers the optimum barrier protection against corrosion.
- Fully reconstructs the coating of three-layer coated pipes**  
Thus, the HTLP allows the pipeline to have a virtually monolithic coating system.
- Dimpled backing provides a "permanent change" indicator for application of heat**  
Ensures correct application heat & allows easy post-heat inspection.  
Reliable inspectability at any time.

## Product selection guide

	HTLP80
<b>Max operating temperature</b>	85°C (185°F)
<b>Compatible line coatings</b>	PE, FBE, Coal Tar, DFBE
<b>Min preheat temperature</b>	70°C (158°F)
<b>Recommended pipe preparation</b>	SA 2½
<b>Soil stress restrictions</b>	None
<b>Performance</b>	EN 12068 Class C60 UV Class C80 UV

## Product thickness

	/B	/1-1.5	/1.2-1	/1.4-1	/C	/1.4-1.8
Backing (as supplied)	0.030 in. 0.75 mm	0.030 in. 0.75 mm	0.035 in. 0.9 mm	0.041 in. 1.04 mm	0.041 in. 1.04 mm	0.041 in. 1.04 mm
Backing (fully free recovered)	0.039 in. 1.0 mm	0.039 in. 1.0 mm	0.047 in. 1.2 mm	0.055 in. 1.4 mm	0.055 in. 1.4 mm	0.055 in. 1.4 mm
Adhesive (as supplied)	0.039 in. 1.0 mm	0.060 in. 1.5 mm	0.039 in. 1.0 mm	0.039 in. 1.0 mm	0.060 in. 1.5 mm	0.071 in. 1.8 mm

## Product properties: HTLP


Property	Test method	Typical Value HTLP80
<b>Backing</b>		
Tensile strength	ASTM D-638	3300 psi (22.8 MPa)
Elongation	ASTM D-638	600%
Hardness, Shore D	ASTM D-2240	55
Shrink force	ASTM D-638, 150°C (302°F)	40 psi
Dielectric strength	ASTM D-149	900 volts/mil (35 KV/mm)
Moisture absorption	ASTM D-570	0.04%
<b>Adhesive</b>		
Softening point	ASTM E-28	120°C (248°F)
Lap shear	ASTM D-1002	750 psi @ 23°C (73°F) 65 psi @ 80°C (176°F)
	EN 12068, @ 10 mm (0.40")/min.	0.19 N/mm <sup>2</sup> @ 80°C (176°F)
<b>Sleeve</b>		
Peel to Steel	ASTM D-1000 EN 12068, @ 10 mm (0.40")/min.	21 lbs/in. width 7.7 N/mm
Cathodic disbondment	ASTM G-42, 30 days	12 mm radius @ 80°C (176°F)
Hot water immersion	ASTM D-870, 120 days	no delamination, no blisters or water ingress, @ 80°C (176°F)
Soil stress creep resistance	TP-206 80°C (176°F)	0.003 mm (0.0001 in.)
Low temperature flexibility	ASTM D-2671-C	-25°C (-13°F)
Impact resistance	ASTM G-14 EN 12068, class C	95 in-lbs > 15 Nm *
Penetration resistance	ASTM G-17, @ 80°C EN 12068, Class C	no holidays @ 10.000 volts > 0.6 mm * @ 80°C (176°F)

\* Construction /1-1.5 or thicker

## Ordering information

### HTLP type products are available:

- as cut piece (pre-cut sleeve with separate closure patch)
- as Uni-sleeve (pre-cut sleeve with pre-attached closure patch)
- as a roll (closure patches to be ordered separately)




Select sleeve width that will overlap onto the mill-applied coating by **2 inches** (50 mm) minimum on each side of the weld joint. Take a 10% shrinkage during installation of sleeve width into account when calculating the minimum sleeve width.

### \* Cut piece / Uni-sleeve

**Example: HTLP80-16000X17/B (/UNI)**

Standard Ordering options			
16000	Outside pipe diameter in mills	2.375" – 100.000" (DN50 – DN2500)	
17	Sleeve width in inches (Sw)	11" (11.25 or 285 mm) <sup>(1)(2)</sup> , 17" (17.75 or 450 mm) <sup>(1)</sup> , 20" (20.25 or 514 mm) <sup>(1)(2)</sup> 24" (23.5 or 600 mm) <sup>(1)</sup> , 34" (34.25 or 870 mm) <sup>(1)</sup>	
/B	Product thickness	/B, /1-1.5, /1.2-1, /1.4-1, /C, /1.4-1.8	
/UNI	Designates pre-attached closure	Optional	




<sup>(1)</sup> nominal width <sup>(2)</sup> not standard in all countries

### \* Roll form (closure patches to be ordered separately)

**Example: HTLP80-20x100/1-1.5-RL**

Standard Ordering options			
20	Roll width in inches (Sw)	11" (11.25 or 285 mm) <sup>(1)(2)</sup> , 17" (17.75 or 450 mm) <sup>(1)</sup> , 20" (20.25 or 514 mm) <sup>(1)(2)</sup> 24" (23.5 or 600 mm) <sup>(1)</sup> , 34" (34.25 or 870 mm) <sup>(1)</sup>	
100	Roll length in feet (Sl)	100 ft (= 30 m), 66 ft (= 20 m, for 34" (870 mm) width)	
/B	Product thickness	/B, /1-1.5, /1.2-1, /1.4-1, /C, /1.4-1.8	




<sup>(1)</sup> nominal width <sup>(2)</sup> not standard in all countries

### \* Closure patch

**Example: WPCP-IV-4X17**

4	Closure patch width in inches (Pw)	4" (100 mm), 5" (125 mm), 6" (150 mm), 8" (200 mm)	
17	Closure patch length in inches (Pl)	11" (11.25 or 285 mm) <sup>(1)(2)</sup> , 17" (17.75 or 450 mm) <sup>(1)</sup> , 20" (20.25 or 514 mm) <sup>(1)(2)</sup> 24" (23.5 or 600 mm) <sup>(1)</sup> , 34" (34.25 or 870 mm) <sup>(1)</sup>	



<sup>(1)</sup> nominal width <sup>(2)</sup> not standard in all countries

Sleeve cut lengths and appropriate closure patch widths depend on the pipe size and product construction, see latest application table AT-GIRTHWELD. For proper product installation, see latest installation instruction.

**HTLP type products are installed with epoxy primer: HTLP80 is installed with S1301-M or S1401 primer.**

**Epoxy Primers are ordered separately. For more ordering information on epoxy primers see latest DS-S1239, DS-S1301M and DS-S1401. As field application of primers may vary, consult a Berry Plastics CPG Representative or Authorized Distributor for rate of coverage guidance**

Berry Plastics warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the technical data sheet when used in compliance with Berry Plastics written instructions. Since many installation factors are beyond the control of Berry Plastics, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in this technical data sheet is to be used as a guide and is subject to change without notice. This technical data sheet supersedes all previous data sheets on this product.



**CORROSION PROTECTION GROUP**

[www.berrycpg.com](http://www.berrycpg.com)

Local Distributor / Representative:

For contact details of local Distributors / Representatives  
Please visit [www.berrycpg.com](http://www.berrycpg.com).

Headquarters : Berry Plastics Tapes & Coatings Division, Franklin MA, USA

Franklin, MA, USA  
Tel: +1 508 918 1714  
US Toll Free: +1 800 248 0149  
Fax: +1 508 918 1910  
CPG@berryplastics.com

Houston, TX, USA  
Tel: +1 713 676 0085  
US Toll Free: 01 888 676 7202  
Fax: +1 713 676 0086  
CPGH@berryplastics.com

Tijuana, Mexico  
Tel USA +1 858 633 9797  
Fax US: +1 858 633 9740  
Tel Mexico: +52 664 647 4397  
Fax Mexico: +52 664 647 4370  
CPGTJ@berryplastics.com

Aarschot, Belgium  
Tel: +32 16 55 36 00  
Fax: +32 16 55 36 74  
CPGE@berryplastics.com

Baroda, India  
Tel: +91 2667 264721  
Fax: +91 2667 264724  
CPGIN@berryplastics.com